

UNCLASSIFIED

Defense Technical Information Center  
Compilation Part Notice

ADP011919

TITLE: Study of the Elastic and Elastooptic Properties of  $\text{Zn}[1-x]\text{Be}[x]\text{Se}$  Mixed Crystals by Brillouin Scattering Method

DISTRIBUTION: Approved for public release, distribution unlimited

This paper is part of the following report:

TITLE: International Conference on Solid State Crystals 2000: Growth, Characterization, and Applications of Single Crystals Held in Zakopane, Poland on 9-12 October 2000

To order the complete compilation report, use: ADA399287

The component part is provided here to allow users access to individually authored sections of proceedings, annals, symposia, etc. However, the component should be considered within the context of the overall compilation report and not as a stand-alone technical report.

The following component part numbers comprise the compilation report:  
ADP011865 thru ADP011937

UNCLASSIFIED

# Study of the elastic and elastooptic properties of $\text{Zn}_{1-x}\text{Be}_x\text{Se}$ mixed crystals by Brillouin scattering method

P. Ziobrowski <sup>a\*</sup>, M. Szybowicz <sup>a</sup>, M. Drozdowski <sup>a</sup>, F. Firszt <sup>b</sup>, S. Łęgowski <sup>b</sup>, J. Szatkowski <sup>b</sup>

<sup>a</sup>Faculty of Technical Physics, Poznan University of Technology, Piotrowo 3, 60-965 Poznań, Poland

<sup>b</sup>Institute of Physics, N. Copernicus University, Grudziądzka 5, 87 - 100 Toruń, Poland

## ABSTRACT

In this paper we report experimental results concerning the elastic and elastooptic properties of  $\text{Zn}_{1-x}\text{Be}_x\text{Se}$  mixed crystals grown by high pressure Bridgman technique. Using Brillouin scattering method some of the elastic and elastooptic constants of  $\text{Zn}_{1-x}\text{Be}_x\text{Se}$  crystals with different Be content have been determined at room temperature. It has been revealed that the elastic and elastooptic properties strongly depend on the content of Be.

**Keywords:** II-VI mixed crystals,  $\text{Zn}_{1-x}\text{Be}_x\text{Se}$ , elastic and elastooptic properties, Brillouin scattering.

## 1. INTRODUCTION

There has been a considerable interest in the physical properties of wide gap II-VI mixed crystals containing Mg or Be.  $\text{Zn}_{1-x}\text{Be}_x\text{Se}$  solid solution is promising material for construction blue-green laser diodes.<sup>1,2</sup> These compounds are interesting in the context of control of band gap energies, lattice constants as well as elastic and elastooptic properties.  $\text{Zn}_{1-x}\text{Be}_x\text{Se}$  mixed crystals have regular structure, belonging to the  $T_d^2$  space group at room temperature. Recently, some of the physical properties of  $\text{Zn}_{1-x}\text{Be}_x\text{Se}$  crystals have been studied using different experimental techniques, such as Raman spectroscopy, photoluminescence and photoacoustic investigations.<sup>3-8</sup> In this paper we report the preliminary study of the elastic and elastooptic properties of  $\text{Zn}_{1-x}\text{Be}_x\text{Se}$  mixed crystals with different Be content using Brillouin scattering method.

## 2. EXPERIMENT

$\text{Zn}_{1-x}\text{Be}_x\text{Se}$  crystals were grown from the melt by the modified high pressure Bridgman method described in details elsewhere.<sup>9</sup> Their composition was determined by chemical wet analysis. The samples used in Brillouin scattering experiment were ground and mechanically polished to the optical quality. They were cut to the sizes of 3 mm x 4 mm x 5 mm, with faces perpendicular to the [100], [010] and [001] directions.




Fig. 1. Schematic picture of the spectrometer used in Brillouin experiment.

The Brillouin polarized spectra were measured at RT using experimental procedure described elsewhere.<sup>10</sup> The schematic picture of the experimental set-up is presented in Fig.1. An Ar ion laser operating on the 488nm line was used as a source of light. It provided 100mW of cw power during operation on a single mode. The scattered radiation was observed at right angle to the incident beam. As a standard we have employed quartz for which the Rayleigh ratio  $R_{st}$  of the longitudinal phonon propagating along [100] direction is known from the literature.<sup>11</sup> The calculation of the Brillouin lines parameters has been performed using curve fitting method. To ensure greater certainty, we made a minimum of 5 separate recordings for each scattering geometry. The estimated error of  $C_{ij}$  does not exceed 1% and 5% in the case of  $p_{ij}$ .

### 3. RESULTS AND DISCUSSION

Using Brillouin scattering method we have studied the elastic and elastooptic properties of  $Zn_{1-x}Be_xSe$  mixed crystals with different Be content. The scattering geometries used in Brillouin experiment are described in Table 1. For our study we have chosen the longitudinal (L) and transverse ( $T_2$ ) acoustic phonons propagating in  $[01\bar{1}]$  direction.

The data which served as a basis for the determination some of the elastic and elastooptic constants of  $Zn_{1-x}Be_xSe$  mixed crystals are listed in Table 2. The phase velocity for longitudinal and transverse acoustic modes deduced from Brillouin spectra are also presented in Table 2.

The typical Brillouin spectra of  $Zn_{1-x}Be_xSe$  mixed crystals with different Be content obtained for longitudinal (L) and transverse ( $T_2$ ) acoustic phonons propagating in  $q=[01\bar{1}]$  direction at room temperature are presented in Fig. 2.




Fig. 2. The Brillouin spectra of  $Zn_{1-x}Be_xSe$  mixed crystals with different Be content obtained for the acoustic phonon propagating in  $[01\bar{1}]$  direction.

Table 1. Scattering geometries used in Brillouin experiment

$k_i = [001]$ $k_s = [010]$	$q$	$L$ $u = [01\bar{1}]/\sqrt{2}$ $\rho V^2 = (C_{11} + C_{12} + 2C_{44})/2$	$T_2$ $u = [100]$ $\rho V^2 = C_{44}$
$d_i = [001]$ $d_s = [001]$	$[01\bar{1}]/\sqrt{2}$	$p_{12}^2$	0
$d_i = [001]$ $d_s = [110]/\sqrt{2}$	$[01\bar{1}]/\sqrt{2}$	0	$p_{44}^2/2$

Table 2. The data which served as a basis for determination some of the elastic and elastooptic constants of  $Zn_{1-x}Be_xSe$  mixed crystals.

X	$\rho$ [g/cm <sup>3</sup> ]	N	$V_L$ [m/s]	$V_{T_2}$ [m/s]
0	5.269	2.784	4422	2418
0.12	5.194	2.760	4557	2727
0.25	5.102	2.734	4179	2851

### 3.1. Study of the elastic properties

$Zn_{1-x}Be_xSe$  mixed crystals crystallize in the regular structure ( $T_d^2$  space group). They have three independent elastic constants:  $C_{11} = C_{22} = C_{33}$ ,  $C_{44} = C_{55} = C_{66}$ ,  $C_{12} = C_{13} = C_{23}$ .<sup>12</sup>

Velocities  $V_j$  of the transverse and longitudinal acoustic phonons propagating along  $[01\bar{1}]$  direction in  $Zn_{1-x}Be_xSe$  mixed crystals with different Be content were determined first. These velocities were deduced from the measured frequency shift  $\Delta\omega_B$  using the Brillouin equation, which in the case of  $90^\circ$  scattering geometry takes the form:

$$\Delta\omega_B = V_j \omega_i [(n^i)^2 + (n^s)^2 - 2 n^i n^s \cos \Theta]^{1/2} / c \quad (1)$$

where  $\omega_i$  is the frequency of the incident light,  $n^i$  and  $n^s$  are the refractive indices for the incident and scattered light, respectively and  $\Theta$  is the angle between the incident and scattered beams.

The velocities were then used to estimate the elastic constants  $C_{ij}$ . The elastic constants can be determined from the solution of the equation of motion, which is given by:

$$|C_{ijk1} q_j q_k - \rho V^2 \delta_{i1}| = 0 \quad (2)$$

Here  $q_j$ ,  $q_k$  are the direction cosines of the phonon wave-vector  $q$ ,  $\rho$  is the density of the crystal and  $C_{ijkl}$  are the elastic constants.

Our study enabled us to estimate the values of the  $(C_{11} + C_{12} + 2C_{44})/2$  and  $C_{44}$  elastic constants. Obtained results are presented in Fig. 3a. It can be seen that the elastic properties of  $Zn_{1-x}Be_xSe$  mixed crystals strongly depend on Be content. The value of the  $(C_{11} + C_{12} + 2C_{44})/2$  decreases, while the value of  $C_{44}$  elastic constant increases with the increase of Be content.

### 3.2. Study of the elastooptic properties

$Zn_{1-x}Be_xSe$  mixed crystals belonging to the regular structure ( $T_d^2$  space group) have three independent elastooptic constants:  $p_{11} = p_{22} = p_{33}$ ,  $p_{44} = p_{55} = p_{66}$ ,  $p_{12} = p_{13} = p_{23}$ .<sup>12</sup> In order to determine the elastooptic properties of  $Zn_{1-x}Be_xSe$  mixed crystals with different Be content, we used a substitution technique proposed by Cummins and Shoen<sup>11</sup>, and developed by Nelson and Lax.<sup>13</sup> In this method the Brillouin spectrum of the crystal under study is compared to that of a standard scatterer whose

Rayleigh ratio  $R_{st}$  is known. If  $I$  is the observed (integrated) intensity of the Brillouin line in the sample spectrum while  $I_{st}$  is the intensity of the Brillouin line in the spectrum of the standard scatterer, the Rayleigh ratio  $R$  of the sample is given by:

$$R = R_{st} (I / I_{st}) = R_{st} J \quad (3)$$

Using Nelson and Lax's approach<sup>13</sup>, the formula for Rayleigh ratio can be written as:

$$R = (\pi^2 kT / 2 \lambda^4) BCF \quad (4)$$

where, for 90-degree scattering geometry,  $C$  is given by :

$$C = (n^i n^s)^3 \cos \delta^i \cos \delta^s / \rho V^2 \quad (5)$$

and  $F$  is given by :

$$F = |d_m^s p_{mnkl} d_n^i u_k q_l|^2 \quad (6)$$

In Eqs (4) - (6):  $B$  is geometric factor which is assumed to be equal for the unknown sample and the standard,  $\delta^{is}$  is the angle between the Poynting vector and the wave-vector of the incident/scattered beam,  $d_m^s$ ,  $d_n^i$  describe the polarization vector of the scattered and incident waves, respectively,  $n^{is}$  is the appropriate refractive index,  $p$  is the effective elastooptic tensor,  $u_k$  is the component of the atomic displacement vector and  $q_l$  is the component of the phonon wave-vector.

The appropriate elastooptic constant  $p_{ij}$  can be determined from equation:

$$F / F_{st} = J C_{st} / C \quad (7)$$

From our study the values of  $p_{12}$  and  $p_{44}$  elastooptic constants were determined. The obtained results are presented in Fig.3b. It can be seen that in the investigated range of composition the elastooptic properties of  $Zn_{1-x}Be_xSe$  mixed crystals depend on Be content noticeably. The value of the  $p_{12}$  decreases, while the value of  $p_{44}$  elastooptic constant increases with the increase of Be content.




Fig. 3. The dependence of the : a) -  $(C_{11} + C_{12} + 2C_{44})/2$  and  $C_{44}$  elastic constants and b) -  $p_{12}$  and  $p_{44}$  elastooptic constants for  $Zn_{1-x}Be_xSe$  mixed crystals as a function of Be content obtained for acoustic phonon propagating in direction  $[01\bar{1}]$  at room temperature.

#### 4. CONCLUSIONS

Using Brillouin scattering measurements some of the elastic and elastooptic constants have been determined. It has been revealed, that the elastic and elastooptic properties of  $\text{Zn}_{1-x}\text{Be}_x\text{Se}$  crystals strongly depend on Be content. However, the nature of this phenomenon is still not well recognized. Its qualification needs further Brillouin scattering study and this is now in progress.

#### ACKNOWLEDGEMENTS

The authors would like to thank MSc. Barbara Sekulska from Institute of Physics N. Copernicus University for technical assistance.

This work was supported in part by the Research Project TB-64-001/2000/DS of Poznań University of Technology and grant nr 321-F of N. Copernicus University.

#### REFERENCES

1. G. Landwehr, F. Fischer, T. Baron, T. Litz, A. Waag, K. Schül, H. Lugauer, T. Gerhard, M. Keim and U. Lunz, "Recent Results on Beryllium Chalcogenides", *Phys. stat. sol (b)* **202**, pp. 645-655, 1997.
2. S.O. Ferreira, H. Sitter, W. Fashinger, R. Krump and G. Brunthaler, "Type I – type II band offset transition of the  $\text{ZnMgSe-ZnTe}$  system" *J. Cryst. Growth* **146**, pp. 418-421, 1995.
3. M. Kozielski, M. Szybowicz, F. Firszt, S. Łęgowski, H. Męczyńska, J. Szatkowski, W. Paszkowicz, "Study of the  $\text{A}_{1-x}\text{B}_x\text{C}$  Mixed Crystals by Raman Scattering," *Cryst. Res. Technol.* **34**, pp. 699-702, 1999.
4. M. Szybowicz, M. Kozielski, F. Firszt, S. Łęgowski, H. Męczyńska, J. Szatkowski, W. Paszkowicz, "Study of  $\text{Zn}_{1-x}\text{Mg}_x\text{Se}$  and  $\text{Zn}_{1-x}\text{Be}_x\text{Se}$  semiconducting crystals by Raman scattering," *Opto-Electr. Rev.* **7**, pp. 103-106, 1999.
5. F. Firszt, S. Łęgowski, H. Męczyńska, J. Szatkowski, W. Paszkowicz, K. Godwod, J. Domagała, M. Kozielski, M. Szybowicz, M. Marczak, "Structure, Luminescence and Lattice Hardening of Be-rich  $\text{Zn}_{1-x}\text{Be}_x\text{Se}$  Bulk Crystals" Proceedings of the 2<sup>nd</sup> International Symposium on Blue Laser and Light Emitting Diodes, Chiba, Japan 1998.
6. F. Firszt, S. Łęgowski, H. Męczyńska, B. Sekulska, J. Szatkowski, J. Zakrzewski, and W. Paszkowicz "Photoluminescence and photoacoustic investigations of beryllium and magnesium containing wide-gap II-VI mixed crystals" *Acta Phys. Polon.* **A95**, pp. 991-996 1989.
7. I.F. Chang, S.S. Mitra, "Long wavelength optical phonons in mixed crystals," *Adv. Phys.* **20**, pp. 359-403, 1971.
8. M. Kozielski, M. Szybowicz, "Temperature and excitation study of the  $\text{A}_{1-x}\text{B}_x\text{C}$  crystals by Raman scattering method", *Proc. Fifth International Conference on Intermolecular Interactions in Matter 1999*, pp. 144 -147, Eds. K. Sangwal, E. Jartych and W. Polak, Politechnika Lubelska, Lublin, 1999.
9. J. Szatkowski, F. Firszt, H. Męczyńska and S. Łęgowski, "Electrical and optical properties of  $\text{ZnSe:Mg}$  crystals," *Acta Phys. Pol.* **A84**, pp. 531-534, 1993.
10. M. Drozdowski, P. Ziobrowski, K. Łapsa, M. Kozielski and W. Bala, "Study of elastic properties of n-ZnSe single crystals by Brillouin scattering", *Proc. SPIE Vol.* **2373**, pp. 277-282, 1995.
11. H.Z. Cummins and P.E. Schoen, in "Laser Handbook", ed. by F.T. Arecchi and E.D. Schultz-Dubois, North-Holland, Amsterdam, 1972.
12. J.F. Nye, in "Physical Properties of Crystals", Clarendon Press, Oxford, 1957.
13. D.F. Nelson and M. Lax, "Theory of the photoelastic interaction," *Phys. Rev. B*, **3**, pp. 2778-2779, 1971.
14. F.C. Peiris, S. Lee, U. Bindley and J.K. Furdyna, "ZnMgSe/ZnCdSe and ZnMgSe/ZnSeTe distributed Bragg reflectors grown by molecular beam epitaxy," *J. Appl. Physics*, **86**, pp. 719-724, 1999.
15. M. Gonzales-Diaz, P. Rodriguez-Hernandez and A. Muno, "Elastic constants and electronic structure of beryllium chalcogenides BeS, BeSe, and BrTe from first-principles calculations," *Phys. Rev. B*, **55**, pp. 14043-14046, 1997.